

NACURE® 3525 Blocked Catalyst



Norwalk, CT 06852 (800) 431-7900 Fax: (203) 866-1268

E-Mail: coatings@kingindustries.com

NACURE 3525 is an amine neutralized Dinonylnaphthalenedisulfonic acid (DNNDSA) catalyst that utilizes a slower releasing amine for higher bake temperatures. NACURE 3525 is formulated for increased solubility, especially in high solids polyester and alkyd formulations.

ADVANTAGES: Good adhesion and salt spray resistance

Excellent water resistance

No wrinkling in most high solids coatings

TYPICAL Appearance Clear, amber liquid

PROPERTIES: % Active 25 pH (1:1 with DI water) 7.7

Weight per gallon, 25°C 7.7

Volatile Isopropanol/isobutanol

SOLUBILITY: Soluble in water, alcohols, glycol ethers, glycols and ketones. Partially soluble in

esters. Insoluble in aromatic and aliphatic hydrocarbons.

APPLICATIONS: Metal decorating

Coil coatings

Automotive topcoats

Can coatings
Appliance finishes
General industrials
Electrostatic spray

TYPICAL USAGE

LEVELS:

0.5 to 2.0 % as supplied on total resin solids.

INCORPORATION: May be added to the coating as supplied or pre-diluted with alcohol.

SHELF LIFE: 18 months from the date of manufacture, when stored at ambient conditions in the

original container.

HANDLING &NACURE 3525 is classified as a flammable liquid. Safe handling of this product storage should include the use of safety glasses and gloves. Avoid breathing vapors - us

should include the use of safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. Product should be stored in lined or glass containers.

Refer to MSDS for detailed information.

REGULATORY: Please refer to Section 15 of the Material Safety Data Sheet for information.

File: NACURE 3525 Issue Date: 12/15/00 Supersedes: 5/6/97

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.