

Product Data Sheet

NACURE[®] 2547 Blocked Catalyst



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

NACURE 2547 is an amine blocked para -Toluenesulfonic acid (p-TSA) catalyst that is diluted with water for easier incorporation into aqueous systems.

ADVANTAGES: Solubility in waterborne systems
Excellent cure response and viscosity stability

TYPICAL PROPERTIES:	Appearance	Clear, colorless liquid
	% Active	25
	pH (as supplied)	8.6
	Weight per gallon, 25°C	9.18 lbs.
	Volatile	Water
	Gardner color	1

SOLUBILITY: Soluble in water, alcohols, glycols, and glycol ethers. Insoluble in esters, ketones, aromatic and aliphatic hydrocarbons.

APPLICATIONS: Waterborne general industrial

**TYPICAL USAGE
LEVELS:** 0.5 - 2.0% as supplied on total resin solids.

INCORPORATION: May be added to the coating with agitation as supplied or pre-diluted with water.

SHELF LIFE: 18 months from the date of manufacture, when stored at ambient conditions in the original container.

**HANDLING &
STORAGE:** Safe handling of this product should include the use of safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. Product should be stored in lined or glass containers away from sunlight and excessive heat. Refer to MSDS for detailed information.

REGULATORY: Please refer to Section 15 of the Material Safety Data Sheet for information.

File: N-2547

Issue Date: 4/22/02

Supersedes: 1/17/97

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.