

## Technical Leaflet

# WorléeCryl 8470

Art.-No. 212054-01031

Revision: 09.11.09

W`Cryl 8470 is a acrylic resin solution. As neutralization agent dimethyl ethanol amine was used. The acrylic resin has an acid value of 85 and a glass transition temperature of 92 °C.

### Technical Data:

Non volatile content DIN EN ISO 3251, part 1	25% ± 1
pH-value DIN ISO 976	8.0 - 9.0
Density DIN EN ISO 2811-1	approx. 1.04 g/cm <sup>3</sup>
Viscosity 20 °C, Brookfield, DIN EN ISO 2555	< 500 mPa·s
Freeze-/thaw stability	3 cycles
<b>Delivery form</b>	25 % in water

The storage stability in the originally closed barrel is at a storage temperature from + 5 to + 25 °C six months, counted from the day of the delivery ex works.