

Technical Leaflet

WorléeKyd B 6301

Art.-No. 111020-07695

Revision: 19.11.2018

W´Kyd B 6301 is a low viscous, long oil air-drying alkyd resin for the production of **low VOC decorative and house paints**.

Technical Data:

Oil type	special vegetable fatty acids
Oil content	approx. 64%
Acid value, on solids, DIN EN ISO 3682	< 18
Colour, Gardner, 70% in dearomat. HC 160 - 200, DIN ISO 4630	< 10
Flow time, 20 °C, 70% in dearomat. HC 160 - 200, DIN 53211-4	60 - 80 s
Delivery form	approx. 100%

Solubility:

W´Kyd B 6301 is well soluble in aromatic and aliphatic hydrocarbons and in dearomatized white spirits and isoparaffines.

Driers:

Following driers are recommended for W´Kyd B 6301:

0.04 - 0.07% Co
0.10 - 0.30% Ca
0.04 - 0.10% Zr

(metal calculated on solid alkyd resin)