

## Technical Leaflet

# WorléeCryl L 2380

Art.-No. 112003-08193

Revision: 04.04.2017

W´Cryl L 2380 is a physically drying thermoplastic acrylic resin for different coating systems, for improving hardness, gloss and adhesion.

### Technical Data:

Non volatile content, 1h/125 °C, DIN EN ISO 3251	50% ± 1
Acid value, on solids, DIN EN ISO 3682	max. 3
Colour, Gardner, delivery form, DIN ISO 4630	max. 3
Viscosity, Rheometer, 20 °C, C 35/1°, 500 s <sup>-1</sup>	max. 1,000 mPa·s
Glass transition temperature	83 °C
<b>Delivery form</b>	50% in deaomat. HC 160 - 200

### Compatibility:

W´Cryl L 2380 is compatible with alkyd resins.

### Solubility:

W´Cryl L 2380 is soluble in ketones, esters, aromatic and deaomatized hydrocarbons as well as isoparaffines. W´Cryl L 2380 is insoluble in alcohols and water.