

Product Data Sheet

NACURE[®] 4000 Alkyl Acid Phosphate Catalyst



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

NACURE 4000 is an alkyl acid phosphate catalyst. It is a weak acid catalyst recommended for use with high -NH/polymeric melamines and phenolic crosslinkers.

ADVANTAGES: Good package stability
Broad solubility
Good adhesion

CHEMICAL COMPOSITION: Alkyl Acid Phosphate

TYPICAL PROPERTIES:	Appearance	Clear, light straw liquid
	% Active	100
	Acid number	650
	Specific gravity, 25° C	1.42
	Weight/gallon, 25° C	11.8 lbs.

SOLUBILITY: Soluble in glycol ethers, glycols, esters, ketones, water and aromatic hydrocarbons.
Insoluble in aliphatic hydrocarbons.

APPLICATIONS: Wood coatings
General industrials
Plastic coatings

SHELF LIFE: 18 months from date of manufacture when stored at ambient conditions in the original container.

HANDLING: NACURE 4000 is classified as a corrosive liquid. Safe handling of this product should include the use of safety glasses and gloves. Avoid breathing vapors- use with adequate ventilation. Consult your MSDS for more information.

REGULATORY: Please refer to section 15 of the material safety data sheet for information.

File: NACURE 4000

Issue Date: 1/19/10

Supersedes:

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.