

Technical Leaflet

WorléeThix L 8050

Art.-No. 111030-12787

Revision: 07.03.12

W^oThix L 8050 is a thixotropic long oil alkyd resin based on linseed oil which is mostly used for wood glazings.

Technical Data:

Oil length	approx. 80%
Oil type	linseed oil fatty acid
Acid value, on solids, DIN EN ISO 3682	max. 15
Viscosity, 20 °C, delivery form	thixotropic gel
Colour, Gardner, delivery form, DIN ISO 4630	max. 10
Delivery form	approx. 100 %

Storage:

The storage stability in the originally closed barrel is at a storage temperature from + 5 to + 25 °C six months, counted from the day of the delivery ex works.