

Technical Leaflet

WorléeKyd BT 5001

Art.-No. 111010-13216

Revision: 07.03.12

W`Kyd BT 5001 is a medium oil, fast drying alkyd resin. The main application is for air and forced drying industrial, vehicle and machine paints, as well as for low VOC dearomatized d.i.y. and house paints.

Technical Data:

Non volatile content, 1h/125 °C, DIN EN ISO 3251	65% ± 1
Content of phthalic acid anhydride	approx. 24%
Oil type	special vegetable fatty acids
Oil content	approx. 50%
Acid value, on solids, DIN EN ISO 3682	max. 12
Colour, Gardner, 50% in dearomat. HC 160 - 200, DIN ISO 4630	max. 10
Flow time, 20 °C, 50% in dearomat. HC 160 - 200, DIN 53211-4	60 - 70 s
Delivery form	65% in dearomat. HC 160 - 200