

## Technical Leaflet

# WorléeKyd SB 6401

Art.-No. 111020-15422

Revision: 28.06.2022

WorléeKyd SB 6401 is a low viscous, long-oil, air drying alkyd resin for the manufacture of low VOC decorative and house paints.

### Technical Data:

Non-volatile content, 1h/125 °C, DIN EN ISO 3251	90% ± 1
Oil type	special vegetable fatty acids
Oil content	approx. 64%
Acid value, on solids, DIN EN ISO 2114	max. 18
Colour, Gardner, 70% in dearomat. HC 180-220, DIN ISO 4630	max. 10
Viscosity, Rheometer, 20 °C, C 35/1°, 250 s <sup>-1</sup>	5,000 - 9,000 mPa·s
<b>Delivery form</b>	90% in dearomat. HC 180-220

### Shelf Life:

The storage stability of WorléeKyd SB 6401 in the originally closed barrel is at a storage temperature from +5 to +25 °C six months, counted from the day of the delivery ex works.