



### **Technical Leaflet**

# WorléeCryl 7462 (VP-A 2770/08)

Art.-No. 212052-22112 Revision: 16.08.2021

WorléeCryl 7462 is an aqueous pure acrylic emulsion.

#### **Technical Data:**

Non volatile content, 55% ± 1 DIN EN ISO 3251

Viscosity, Brookfield, 20 °C, max. 1,000 mPa·s

**DIN EN ISO 2555** 

pH-value, DIN ISO 976 7.0 - 8.0

Density, DIN EN ISO 2811-1 approx. 1.06 g/cm<sup>3</sup>

MFFT <1 °C

Minimum film forming temperature

ISO 2115

Freeze-thaw stability protect from freezing

**Delivery form** 55% in water

### **Specific Characteristics:**

High block resistance.

High gloss in emulsion paints.

## **Application and Properties:**

WorléeCryl 7462 is a high solid acrylic dispersion for the formulation of high gloss emulsion paints for the production of very easy processable and DIY lacquer-systems.

The outstanding characteristic of this binder is the high block resistance which is usually demanded for window- and door-application etc.

Wood glazings can be created totally without solvents, pigmented top coats need for the support of the film formation and for the improve of the leveling small parts of high-boiling solvents.

#### **Shelf Life:**

The storage stability of WorléeCryl 7462 in the originally closed barrel is at a storage temperature from +5 to +25 °C six months, counted from the day of the delivery ex works.