

Technical Leaflet

WorléeSol NW 474

Art.-No. 111055-22845

Revision: 06.08.2021

WorléeSol NW 474 is a long-oil, amine and co-solvent free alkyd emulsion.

Technical Data:

Appearance	white, milky liquid
Non volatile content, 1h/125 °C, DIN EN ISO 3251	60% ± 2
Oil content	approx. 74%
Viscosity, Rheometer, 20 °C, C 60/2°, 5 s ⁻¹	max. 1,500 mPa·s
pH-value, DIN ISO 976	< 7
Density, 23 °C, DIN EN ISO 2811-1	1.013 g/cm ³
Delivery form	60% in water

Application and Properties:

WorléeSol NW 474 is suitable for the manufacture of wood impregnations and glazings. A further application field for WorléeSol NW 474 is open time and body improvement of decorative and house paints based on WorléeSol E 150 W by addition of 3 - 10% on total formulation.

Mix well before use.

Recommended Storage and Transport Conditions:

Protect from freezing and avoid direct sunlight.

Shelf Life:

The storage stability of WorléeSol NW 474 in the originally closed barrel is at a storage temperature from +5 to +25 °C nine months, counted from the day of the delivery ex works.