

Technical Leaflet

WorléeCryl 7750

Art.-No. 212052-22881

Revision: 12.12.2022

Aqueous cationic acrylate copolymer dispersion.

Technical Data:

Non volatile content, 1h/125 °C, DIN EN ISO 3251	45% ± 1
Viscosity, 20 °C, DIN EN ISO 2555	max. 500 mPa·s
pH-value, DIN ISO 976	4.0 - 5.0
MFFT, Minimum film forming temperature ISO 2115	< 1 °C
Freeze-thaw stability, ISO 1147	protect from freezing
Delivery form	45% in water

Application and Properties:

WorléeCryl 7750 is characterized by high flexibility and can be used for the formulation of primers and glossy top coats with good insulating properties against wood components.

WorléeCryl 7750 may not be applied together with alkaline systems or additives. The resin will be precipitated if the pH-value is increased.

Shelf Life:

The storage stability of WorléeCryl 7750 in the originally closed barrel is at a storage temperature from +5 to +25 °C six months, counted from the day of the delivery ex works.