

Technical Leaflet

WorléeCryl 7189

Art.-No. 212052-22954

Revision: 12.06.2020

Methacrylic copolymer emulsion.

Technical Data:

Non volatile content, DIN EN ISO 3251	49% ± 1
pH-value, DIN ISO 976	7.0 - 8.0
Density, 20 °C, DIN EN ISO 2811-1	approx. 1.08 g/cm ³
Viscosity, 20 °C, Brookfield, DIN EN ISO 2555	max. 200 mPa·s
Emulsion system	anionic
MFFT, Minimal film forming temperature, ISO 2115	16 °C
Freeze-/thaw stability	protect from freezing
Delivery form	49% in water

Outstanding Characteristics:

Excellent compatibility with alkali and cement.

High flexibility.

Properties and Application:

WorléeCryl 7189 is a binder for the production of synthetic, resin-bound renderings, wall paints, flagstone- and building adhesives. The product features a high initial adhesion and a very fast setting.

WorléeCryl 7189 can also be used for the production of sealing compounds.

Shelf Life:

The storage stability of WorléeCryl 7189 in the originally closed barrel is at a storage temperature from + 5 to + 25 °C six months, counted from the day of the delivery ex works.