

Technical Leaflet

WorléeCryl 7520

Art.-No. 212052-22957

Revision: 07.10.2022

Pure acrylic emulsion.

Technical Data:

Non volatile content DIN EN ISO 3251	50% \pm 1
Viscosity, Brookfield, 20 °C, DIN EN ISO 2555	1,600 - 2,400 mPa·s
pH-value, DIN ISO 976	8.5 - 9.0
Density, DIN EN ISO 2811-1	approx. 1.05 g/cm ³
Emulsion system	anionic
MFFT, Minimum film forming temperature ISO 2115	14 °C
Freeze-thaw stability, ISO 1147	5 cycles
Delivery form	50% in water

Specific Characteristics:

Widely spread compatibility with pigments and fillers.

High gloss, water- and alkali resistance.

Flexible and block resistant in a good balance.

Application and Properties:

WorléeCryl 7520 can be used for the production of emulsion paints interior and exterior use.

Shelf Life:

The storage stability of WorléeCryl 7520 in the originally closed barrel is at a storage temperature from +5 to +25 °C six months, counted from the day of the delivery ex works.