

## Technical Leaflet

# WorléeCryl 7410

Art.-No. 212052-22996

Revision: 07.10.2022

Self cross linking acrylic copolymer emulsion.

### Technical Data:

Non-volatile content, 1h/125 °C, DIN EN ISO 3251	45% ± 1
Viscosity, Brookfield, 20 °C, DIN EN ISO 2555	max. 500 mPa·s
pH-value, DIN ISO 976	8 - 9
Tg (calculated) glass transition temperature	48 °C
MFFT, Minimum film forming temperature ISO 2115	39 °C
Freeze-thaw stability, ISO 1147	protect from freezing
<b>Delivery form</b>	45% in water

### Specific Characteristics:

Chemical resistance.

Alcohol resistance

### Application and Properties:

WorléeCryl 7410 is an acrylic emulsion for the formulation of aqueous wood and furniture lacquers.

### Recommended Storage and Transport Conditions:

Protect from freeze and avoid direct sunlight.

### Shelf Life:

The storage stability of WorléeCryl 7410 in the originally closed barrel is at a storage temperature from +5 to +25 °C six months, counted from the day of the delivery ex works.