

## Technical Leaflet

# WorléeCryl 7135

Art.-No. 212052-23039

Revision: 21.02.2020

Styrene acrylic copolymer emulsion.

### Technical Data:

Non volatile content DIN EN ISO 3251	42% ± 1
pH - Value DIN ISO 976	7.5 - 8.5
Density DIN EN ISO 2811-1	approx. 1.04 g/cm <sup>3</sup>
Viscosity, Brookfield, 20 °C, DIN EN ISO 2555	max. 1,000 mPa·s
Emulsion system	anionic
MFFT, Minimum film forming temperature ISO 2115	39 °C
Freeze-/thaw stability	5 cycles
<b>Delivery form</b>	42% in water

### Outstanding Characteristics:

Excellent adhesion on various substrates.

Very good compatibility with water soluble alkyd resin.

### Properties and Application:

WorléeCryl 7135 has widely spread application facilities for top coats on plastics, metal and wood.

This product can also be used as binding agent for the production of temporary plastic primers.

Last WorléeCryl 7135 is suitable as combining agent for water soluble alkyd resins in hybrid coats.

### Shelf Life:

The storage stability of WorléeCryl 7135 in the originally closed barrel is at a storage temperature from + 5 to + 25 °C six months, counted from the day of the delivery ex works.