

Technical Data Sheet

WorléeCryl 7135

styrene acrylic copolymer dispersion

Art.-No. 212052-23039

update: 20.03.2025

Technical Data:

	Value	Method*
Non-volatile content	41 - 43%	1h/125 °C, DIN EN ISO 3251
Emulsion system	anionic	
Minimum film forming temperature	approx. 39 °C	ISO 2115
Viscosity, Brookfield	≤ 1,000 mPa·s	20 °C, DIN EN ISO 2555
pH-value	8.5 - 9.5	DIN ISO 976
Delivery form	approx. 42% in water	

*according to the respective DIN-Norm

Application and Properties:

WorléeCryl 7135 has widely spread application facilities for top coats on plastics, metal and wood excellent adhesion on various substrates.

This product can also be used as binding agent for the production of temporary plastic primers.

Last WorléeCryl 7135 is suitable as combining agent for water soluble alkyd resins in hybrid coats.

Shelf Life and recommended Conditions for Storage and Transport:

The storage stability of WorléeCryl 7135 in the originally closed container is six months at a storage temperature between +5 and +25 °C, counted from the day of the delivery ex works.