

## Technical Leaflet

# WorléeCryl 7755 (VP-A 3415/11)

Art.-No. 212052-24569

Revision: 13.04.2023

Aqueous cationic acrylate copolymer dispersion.

### Technical Data:

Non-volatile content, 1h/125 °C, DIN EN ISO 3251	40% ± 1
Viscosity, Rheometer, 20 °C, C 60/2°, 50 s <sup>-1</sup>	max. 1,500 mPa·s
pH-value, DIN ISO 976	5.5 - 6.5
MFFT, Minimum film forming temperature ISO 2115	< 1 °C
Freeze-thaw stability	protect from freezing
<b>Delivery form</b>	40% in water

### Specific Characteristics:

Good insulating properties.

Low odor and flexible.

### Application and Properties:

WorléeCryl 7755 is especially suitable for the production of nicotine insulating wall paints and pigmented insulating primers for wood substrates.

### Special Recommendation:

WorléeCryl 7755 may not be applied together with alkali-matched systems or additives. This product has a pH-value of under 7.0. The resin will be precipitated if the pH-value is increased. The use of carbonates should be avoided.

### Shelf Life:

The storage stability of WorléeCryl 7755 in the originally closed barrel is at a storage temperature from +5 to +25 °C six months, counted from the day of the delivery ex works.