

## Technical Leaflet

# WorléeCryl 7755

Art.-No. 212052-24569

Revision: 13.11.2024

Aqueous cationic acrylate copolymer dispersion.

### Technical Data:

Non-volatile content, 1h/125 °C, DIN EN ISO 3251	39 - 41%
Minimum film forming temperature, ISO 2115	< 1 °C
Viscosity, Rheometer, 20 °C, C 60/2°, 50 s <sup>-1</sup>	800 - 2.000 mPa·s
pH-value, DIN ISO 976	5.5 - 6.5
<b>Delivery form</b>	approx. 40% in water

### Application and Properties:

WorléeCryl 7755 is especially suitable for the production of nicotine insulating wall paints and pigmented insulating primers for wood substrates.

WorléeCryl 7755 is low-odour and flexible. The special characteristics of WorléeCryl 7755 also include a good insulating effect.

### Special Notes:

WorléeCryl 7755 may not be applied together with alkali-matched systems or additives. This product has a pH-value of under 7.0. The resin will be precipitated if the pH-value is increased. The use of carbonates should be avoided.

### Shelf Life, recommended Storage and Transport Conditions:

The storage stability of WorléeCryl 7755 in the originally closed barrel is at a storage temperature from +5 to +25 °C six months, counted from the day of the delivery ex works.

Protect from freeze.