

## Technical data sheet

# TIPAQUE R-980

Art. No.: 337002-01358

Version: 08/2021

TIPAQUE R-980 is an after-treated rutile pigment with medium particle size produced by the sulphate process.

### Technical Data:

	Value	Unit	Test Method
TiO <sub>2</sub> - Content	approx.. 93	%	
Aftertreatment inorganic	Aluminium Oxide		
Aftertreatment organic	Polyol		
Oil number	approx. 19	g /100 g Pigment	
Spec. Gravity	approx. 4,1	g/cm <sup>3</sup>	
Particle size	approx. 0,24	µm	
pH value	6,0 – 8,0	10 g/l	
Conductivity	≤ 100	µS/cm	
Resistance	very good		
Delivery form	Powder		

### Application and Properties

TIPAQUE R-980 is characterised by very good hiding power, high tinting strength and excellent gloss. Due to the surface treatment with aluminium oxide and an organic compound, TIPAQUE R-980 has very good weather resistance and easy dispersibility. The pigment results in a unique bluish undertone due to its small particle size.

TIPAQUE R-980 is a multi-purpose grade and can be used in a wide range of applications.

Due to its high resistance, TIPAQUE R-980 is especially indicated for the use in systems to be submitted to severe requirements, e.g.:

Architectural paints, exterior paints where maximum durability is required, but also interior paints, printing inks, powder coatings, various kinds of plastics (rigid and soft PVC, PE, PP, PS, ABS).

**Packaging:**

25-kg-bags

**Recommended storage conditions**

TIPAQUE R-980 should be stored in tightly closed containers in a dry, cool and well ventilated place.