

NACURE[®] 2107

Blocked Acid Catalyst



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

NACURE 2107 is an amine neutralized para-Toluenesulfonic (p-TSA) catalyst designed for fast cure response. It improves metal scratch resistance of acid catalyzed formulations.

ADVANTAGES: Enhanced metal mark resistance
Excellent cure response
Waterborne or high solids coatings

TYPICAL PROPERTIES:	Appearance	Clear, straw liquid
	% Active	25
	pH (1:1 with DI water)	8.6
	Weight per gallon, 25°C	7.55
	Volatile	Isopropanol
	Gardner Color	1

SOLUBILITY: Soluble in water, alcohols, ethers and glycols. Partially soluble in ketones and aromatic hydrocarbons. Insoluble in aliphatic hydrocarbons.

APPLICATIONS: Appliance finishes
Coil coatings
General industrials

TYPICAL USAGE LEVELS: 0.5 -2.0 % as supplied on total resin solids.

INCORPORATION: May be added to the coating with agitation as supplied or pre-diluted with alcohol.

SHELF LIFE: 15 months from the date of manufacture, when stored at ambient conditions in the original container.

HANDLING & STORAGE: NACURE 2107 is classified as a flammable liquid. Safe handling of this product should include the use of safety glasses and gloves. Avoid breathing vapors - use with adequate ventilation. Product should be stored in lined or glass containers away from sunlight and excessive heat. Refer to MSDS for detailed information.

REGULATORY: Please refer to Section 15 of the Material Safety Data Sheet for information.

File: N-2107

Issue Date: 4/29/02

Supersedes: 10/21/97