

Product Data Sheet

K-KAT[®] A209 Urethane Catalyst



Science Road
Norwalk, CT 06852
(800) 431-7900
Fax: (203) 866-1268
E-Mail: coatings@kingindustries.com

K-KAT A209 is a catalyst for the reaction of isocyanate with hydroxyl groups. It is a zirconium chelate complex dissolved in a reactive diluent and t-butyl acetate. K-KAT A209 catalyst is 8 times more active than K-KAT 6212 and can be used as a replacement for this catalyst.

ADVANTAGES:

- Excellent cure response
- Excellent exterior durability
- Does not contribute to the hydrolysis of polyester resins
- Short tack free time at low cure temperature
- High selectivity for -NCO/OH reaction over -NCO/water reaction
- Pot life adjustable with stabilizer

TYPICAL PROPERTIES:	Appearance	Clear, straw liquid
	Volatile	t-butyl acetate
	Specific gravity, 25°C	0.95
	% Active (metal chelate)	14

SOLUBILITY:	Alcohols, esters, ketones	Soluble
	Aromatic hydrocarbon	Soluble
	Glycol ethers and glycol ether acetates	Soluble
	Aliphatic hydrocarbons	Soluble
	Water	Limited, will hydrolyze

APPLICATIONS: Polyurethane coatings, adhesives, RIM, casting resins and polyurethane resin synthesis, water-borne two component coatings and transesterification catalysis.

TYPICAL USAGE LEVELS: 0.05-2.0% on total resin solids. Refer to chart on the back of this page for more information on suggested usage levels.

INCORPORATION: Addition of the catalyst to polyisocyanate is suggested as the best method to assure catalytic activity. See page 2 for complete details.

SHELF LIFE: 12 months from the date of manufacture, when stored at ambient conditions in the original container.

HANDLING & STORAGE: This product is sensitive to moisture. Exposure to atmospheric moisture during storage should be avoided. Consult the MSDS for safe handling. This product is designed to be premixed with the polyisocyanate component or to be added just before application of two component systems. Avoid contact with metals.


REGULATORY: Please refer to Section 15 of the Material Safety Data Sheet for information

File: K-KAT A209

Issue Date: 11/1/2006

Supersedes: 11/30/04

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.



Formulation and Handling Information:

K-KAT[®] A209 catalyst is recommended for application in two component polyisocyanate/hydroxyl systems which require a fast cure rate and reduced reaction with water. K-KAT A209 is therefore suitable for two component high solids coatings or RIM applications where a plural component mixing system is used or where a short potlife is acceptable. The potlife with this catalyst can be increased by adding a diketone like 2,4-pentanedione to the formulation. K-KAT A209 can also be used in the synthesis of polyurethanes where the destruction of the catalyst after PU synthesis is desired. K-KAT A209 is based on a zirconium chelate and is therefore environmentally acceptable. K-KAT A209 catalyst has also shown excellent performance and minimum gassing in two component water-borne coatings. The catalyst should be added to the isocyanate crosslinker. A small level of 2,4-pentanedione added to the polyol component can extend potlife and improve gloss. A higher level of A209 is required in water-borne coatings (0.2-2 % based on resin solids) compared to high solids coatings.

K-KAT A209 operates by a different mechanism compared to common organotin catalysts by activating the hydroxyl groups and not the isocyanate groups. Since K-KAT A209 does not catalyze the hydrolysis of polyester resins there is little or no effect on exterior durability with these systems.

Like most metal chelates K-KAT A209 catalyst is sensitive to moisture and should be added to that part of the system which is water free or one that contains a water scavenger. Water in excess of 0.1% in the system will deactivate the catalyst within several hours. Addition of the catalyst to the polyisocyanate is suggested as the best method to assure catalytic activity. Addition of 2 % of K-KAT A209 to an HDI trimer has exhibited more than two weeks stability at 50°C.

The activity of K-KAT A209 can also be affected by the presence of acids. In the presence of free carboxylic acids the rate of the reaction of the catalyst is substantially reduced. Polyols with an acid number of less than 10 are recommended. Neutralization of the acid with an amine will eliminate this effect of reduced reaction rate. Amines do not function as co-catalysts with A209. Addition of a cycloaliphatic epoxy can also eliminate this reduction in reaction rate. K-KAT A209 may also be deactivated by the presence of phosphoric acid. Some polyether polyols may contain residual phosphoric acid which is added to neutralize the potassium hydroxide used during the manufacturing operation.

K-KAT A209 is not recommended for blocked isocyanates and heat cured applications when the cure temperature exceeds 80°C (176°F). Because of the much higher catalyst concentration in K-KAT A209 in comparison to K-KAT 6212 and 4205, K-KAT A209 can be used with slow reacting isocyanates which would require very high concentrations of the other catalysts.

K-KAT A209 can also be used in transesterification reactions as a replacement for the zirconium 2,4-pentanedione complex. The improved solubility and liquid nature of this catalyst is an advantage in this application.